

## E250BO – Technical Overview

### 1. Chemical & Mechanical Properties

#### A. Chemical Composition

Element	C	Mn	S	P	Si	CE (Max)
Value	0.23	1.50	0.045	0.045	0.45	0.42

#### B. Mechanical Properties

Property	Value
Yield Strength (YS, min)	250 MPa (for ≤ 20 mm thickness)
Tensile Strength (UTS)	410–540 MPa
Elongation (Gauge length 5.65VA)	≥ 23%
Impact Test	Optional, at room temperature

### 2. Equivalent / Alternative Grades

Grade Name	Standard	YS (MPa)	UTS (MPa)	Elongation (%)	C	Mn	Si	P	S
S275JR	EN 10025-2	275	410–560	≥ 20	0.21	1.50	0.50	0.035	0.035
ASTM A36	ASTM	250	400–550	≥ 20	0.26	0.80–1.20	0.40	0.04	0.05
Fe410W	IS 1977	250	410–540	≥ 23	0.23	1.50	0.45	0.045	0.045

### 3. Common Applications

- Structural fabrication (beams, channels, angles)
- Bridges and flyovers
- General construction (buildings, warehouses)
- Equipment and frames
- Railway wagons and rolling stock

### 4. Conforming Standard

- IS 2062:2011 / 2019 (Indian Standard)

- Category: B0 (Sub-quality B, Fully Killed Steel, Impact Optional)

## 5. Disclaimer

All chemical compositions, mechanical properties, dimensions and other technical data presented on this page are provided by Raunaq Steels Trading Pvt. Ltd. for general reference only. While we endeavour to ensure that the information is as accurate and up-to-date as possible, no warranty, express or implied, is given as to its completeness, correctness or fitness for any particular purpose. Raunaq Steels Trading Pvt. Ltd. accepts no liability for any loss or damage arising directly or indirectly from the use of, or reliance upon, the information contained herein.

For authoritative and legally binding specifications, users must refer to the official publications of the relevant standards—such as the BIS, ASTM, EN or JIS standards—available through their respective websites or published documents.