

E250CuC – Technical Datasheet

1. Chemical & Mechanical Properties

A. Chemical Composition

Element	% Composition
Carbon (C)	≤ 0.22%
Manganese (Mn)	≤ 1.35%
Phosphorus (P)	≤ 0.045%
Sulphur (S)	≤ 0.040%
Copper (Cu)	0.20 – 0.35%
Silicon (Si)	≤ 0.45%

B. Mechanical Properties

Property	Value
Yield Strength (YS)	≥ 250 MPa
Tensile Strength (TS)	410 – 540 MPa
Elongation	≥ 22%
Hardness	130 – 170 HB
Impact Test	27J min at -10°C (Charpy V-Notch)

2. Equivalent / Alternative Grades

A. Equivalent Grades Summary

Standard	Grade	Chemical & Mechanical Summary
IS 2062	E250CuC	YS ≥ 250 MPa, TS 410-540 MPa, Cu 0.20-0.35%, impact tested
EN 10025-2	S275J0 + Cu	Similar YS & TS, copper added, impact tested at 0°C
ASTM A36 + Cu	Custom Cu-added A36	Lower tensile strength, similar yield, copper for corrosion resistance

3. Common Applications

- Structural steel in general fabrication and construction
- Bridges and buildings where moderate strength is required
- Weather-resistant steel applications due to copper addition
- Automotive parts and chassis components
- Light to medium machinery parts and fabrication

4. Standard Conformance

IS 2062:2011 – Indian Standard for Hot Rolled Medium and High Tensile Structural Steel.

- Grade Code Meaning:
- E: Killed steel
- 250: Minimum yield strength in MPa
- Cu: Copper added for corrosion resistance
- C: Impact tested at sub-zero temperature (Charpy V-Notch)

5. Disclaimer

All chemical compositions, mechanical properties, dimensions and other technical data presented on this page are provided by Raunaq Steels Trading Pvt. Ltd. for general reference only. While we endeavour to ensure that the information is as accurate and up-to-date as possible, no warranty, express or implied, is given as to its completeness, correctness or fitness for any particular purpose. Raunaq Steels Trading Pvt. Ltd. accepts no liability for any loss or damage arising directly or indirectly from the use of, or reliance upon, the information contained herein.

For authoritative and legally binding specifications, users must refer to the official publications of the relevant standards—such as the BIS, ASTM, EN or JIS standards—available through their respective websites or published documents.