

E300A –Technical Datasheet

1. Chemical & Mechanical Properties

Property	Value
C	≤ 0.22%
Mn	≤ 1.40%
P	≤ 0.045%
S	≤ 0.040%
Si	≤ 0.40%
Cu	0.10 – 0.25%
Yield Strength (YS)	≥ 300 MPa
Tensile Strength (TS)	460 – 590 MPa
Elongation	≥ 21%
Hardness	140 – 170 HB
Impact Test	Optional / Not Required

2. Equivalent / Alternative Grades

Standard	Grade	C (%)	Mn (%)	P (%)	S (%)	Si (%)	Cu (%)	Yield Strength (MPa)	Tensile Strength (MPa)	Elongation / Impact
IS 2062	E300A	≤ 0.22	≤ 1.40	≤ 0.045	≤ 0.040	≤ 0.40	0.10 – 0.25	≥ 300	460 – 590	≥ 21% / Optional
EN 10025-2	S275JR	≤ 0.22	≤ 1.60	≤ 0.035	≤ 0.035	≤ 0.55	-	≥ 275	410 – 560	≥ 23% / 27J @ 20°C
ASTM A36	A36	≤ 0.26	≤ 1.35	≤ 0.040	≤ 0.050	≤ 0.40	-	≥ 250	400 – 550	≥ 23% / 27J @ RT

3. Common Applications

- General structural steel applications
- Building construction
- Bridges and frameworks

- Machinery parts
- Automotive components

4. Standard Conformance

IS 2062:2011 – Indian Standard for Hot Rolled Medium and High Tensile Structural Steel.

Grade Code Meaning:

E: Killed steel; 300: Minimum yield strength in MPa; A: Grade variant

5. Disclaimer

All chemical compositions, mechanical properties, dimensions and other technical data presented on this page are provided by Raunaq Steels Trading Pvt. Ltd. for **general reference only**. While we endeavour to ensure that the information is as accurate and up-to-date as possible, **no warranty, express or implied, is given** as to its completeness, correctness or fitness for any particular purpose. Raunaq Steels Trading Pvt. Ltd. **accepts no liability** for any loss or damage arising directly or indirectly from the use of, or reliance upon, the information contained herein.

For **authoritative** and **legally binding** specifications, users must refer to the **official publications** of the relevant standards—such as the BIS, ASTM, EN or JIS standards—available through their respective websites or published documents