



**RAUNAQ**  
— TRUSTED STEEL —

# E350CuC – Technical Datasheet

## 1. Chemical & Mechanical Properties

### A. Chemical Composition

Element	% Composition
Carbon (C)	≤ 0.20%
Manganese (Mn)	≤ 1.55%
Sulphur (S)	≤ 0.040%
Phosphorus (P)	≤ 0.045%
Copper (Cu)	0.20 – 0.35%
Silicon (Si)	≤ 0.45%

### B. Mechanical Properties

Property	Value
Yield Strength (YS)	≥ 350 MPa
Tensile Strength (TS)	490 – 610 MPa
Elongation	≥ 22%
Hardness	160 – 190 HB
Impact Test	27J min at -20°C (Charpy V-Notch test)

## 2. Equivalent / Alternative Grades

### A. Chemical Composition Comparison

Standard	Grade	C (%)	Mn (%)	P (%)	S (%)	Si (%)	Cu (%)
IS 2062	E350CuC	≤ 0.20	≤ 1.55	≤ 0.045	≤ 0.040	≤ 0.45	0.20 – 0.35
EN 10025-2	S355J2 + Cu	≤ 0.24	≤ 1.60	≤ 0.035	≤ 0.035	≤ 0.55	≥ 0.20
ASTM A572	Gr 50 + Cu	≤ 0.23	≤ 1.35	≤ 0.040	≤ 0.050	≤ 0.40	≥ 0.20
JIS G3106	SM490YB + Cu	≤ 0.20	≤ 1.60	≤ 0.035	≤ 0.035	≤ 0.55	≥ 0.20 (typ.)

## B. Mechanical Properties Comparison

Standard	Grade	Yield Strength (MPa)	Tensile Strength (MPa)	Elongation / Impact
IS 2062	E350CuC	≥ 350	490 – 610	≥ 22%, 27J @ -20°C
EN 10025-2	S355J2 + Cu	≥ 355	470 – 630	≥ 22%, 27J @ -20°C
ASTM A572	Gr 50 + Cu	≥ 345	450 – 620	≥ 21%, 20J @ RT
JIS G3106	SM490YB + Cu	≥ 355	490 – 610	~21%, 27J @ 0°C

## 3. Common Applications

- Railway wagons and coaches
- Weather-resistant steel structures
- Bridges and construction frameworks
- Earth-moving equipment and fabrication
- Marine and industrial containers

## 4. Standard Conformance

IS 2062:2011 – Indian Standard for Hot Rolled Medium and High Tensile Structural Steel.

Grade Code Meaning:

- E: Killed steel
- 350: Minimum yield strength in MPa
- Cu: Copper added for corrosion resistance
- C: Impact tested at -20°C (Charpy V-Notch, min 27J)

## 5. Disclaimer

All chemical compositions, mechanical properties, dimensions and other technical data presented on this page are provided by Raunaq Steels Trading Pvt. Ltd. for **general reference only**. While we endeavour to ensure that the information is as accurate and up-to-date as possible, **no warranty, express or implied, is given** as to its completeness, correctness or fitness for any particular purpose. Raunaq Steels Trading Pvt. Ltd. **accepts no liability** for any loss or damage arising directly or indirectly from the use of, or reliance upon, the information contained herein.

For **authoritative** and **legally binding** specifications, users must refer to the **official publications** of the relevant standards—such as the BIS, ASTM, EN or JIS standards—available through their respective websites or published documents.