



RAUNAQ
— TRUSTED STEEL —

E410C – Technical Datasheet

1. Chemical & Mechanical Properties

Property	Value
C	≤ 0.26%
Mn	≤ 1.60%
P	≤ 0.045%
S	≤ 0.040%
Si	≤ 0.50%
Cu	0.15 – 0.30%
Yield Strength (YS)	≥ 410 MPa
Tensile Strength (TS)	550 – 700 MPa
Elongation	≥ 15%
Hardness	190 – 220 HB
Impact Test	27J min at -10°C (Charpy V-Notch)

2. Equivalent / Alternative Grades

Standard	Grade	C (%)	Mn (%)	P (%)	S (%)	Si (%)	Cu (%)	Yield Strength (MPa)	Tensile Strength (MPa)	Elongation / Impact
IS 2062	E410C	≤ 0.26	≤ 1.60	≤ 0.045	≤ 0.040	≤ 0.50	0.15 – 0.30	≥ 410	550 – 700	≥ 15% / 27J @ -10°C
EN 10025-2	S420J2+Cu	≤ 0.22	≤ 1.60	≤ 0.035	≤ 0.035	≤ 0.55	≥ 0.20	≥ 420	490 – 630	≥ 22% / 27J @ -10°C
ASTM A572	Gr 50+Cu	≤ 0.23	≤ 1.35	≤ 0.040	≤ 0.050	≤ 0.40	≥ 0.20	≥ 345	450 – 620	≥ 21% / 20J @ RT

3. Common Applications

- Weather resistant structures
- Marine applications
- Bridges

- Industrial fabrication
- Railway wagons

4. Standard Conformance

IS 2062:2011 – Indian Standard for Hot Rolled Medium and High Tensile Structural Steel.

Grade Code Meaning:

E: Killed steel; 410: Minimum yield strength in MPa; C: Copper added for corrosion resistance

5. Disclaimer

All chemical compositions, mechanical properties, dimensions and other technical data presented on this page are provided by Raunaq Steels Trading Pvt. Ltd. for **general reference only**. While we endeavour to ensure that the information is as accurate and up-to-date as possible, **no warranty, express or implied, is given** as to its completeness, correctness or fitness for any particular purpose. Raunaq Steels Trading Pvt. Ltd. **accepts no liability** for any loss or damage arising directly or indirectly from the use of, or reliance upon, the information contained herein. For **authoritative and legally binding** specifications, users must refer to the **official publications** of the relevant standards—such as the BIS, ASTM, EN or JIS standards—available through their respective websites or published documents