

S460MC — EN 10149-2 (2013)

1. Chemical & Mechanical Properties

C (%)	Mn (%)	Si (%)	P (%)	S (%)	Yield (MPa)	UTS (MPa)	Elong (%)
0.12	1.60	0.50	0.025	0.015	≥460	520-670	14 / 17

2. Equivalent / Alternative Grades

Grade	Standard	YS	UTS	C max (%)
ASTM A572 Gr60	ASTM A572	415	550	0.23
Strenx 600MC	SSAB	600	750	0.12

3. Common Applications

- Truck side members
- Agricultural equipment
- Cranes (light duty)

4. Standard Conformance

EN 10149-2 : 2013 — High-strength, thermomechanically rolled steels for cold forming

5. Disclaimer

All chemical compositions, mechanical properties, dimensions and other technical data presented on this page are provided by Raunaq Steels Trading Pvt. Ltd. for **general reference only**. While we endeavour to ensure that the information is as accurate and up-to-date as possible, **no warranty, express or implied, is given** as to its completeness, correctness or fitness for any particular purpose. Raunaq Steels Trading Pvt. Ltd. **accepts**

no liability for any loss or damage arising directly or indirectly from the use of, or reliance upon, the information contained herein.

For **authoritative** and **legally binding** specifications, users must refer to the **official publications** of the relevant standards—such as the BIS, ASTM, EN or JIS standards—available through their respective websites or published documents.