

# EN BS 970 EN8A – Technical Datasheet

## 1. Chemical & Mechanical Properties

C (%)	Mn (%)	P (%)	S (%)	Yield (MPa)	Tensile (MPa)	Elongation (%)
0.37–0.45	0.60–1.00	≤0.040	≤0.040	≥280	550–650	≥16

## 2. Equivalent / Alternative Grades

Grade	Chem Note	Yield	UTS
AISI 1040	C 0.37–0.44	Yield ≥415 MPa	UTS ≥620 MPa
DIN C40	C 0.37–0.44	Yield ≥210 MPa	UTS ≥380 MPa
JIS S45C	C 0.42–0.48	Yield ≥490 MPa	UTS ≥686 MPa

## 3. Common Applications

- Welded fabrications
- Pins & studs

## 4. Standard Conformance

BS 970-3:1991 080A40

## 5. Disclaimer

All chemical compositions, mechanical properties, dimensions and other technical data presented on this page are provided by Raunaq Steels Trading Pvt. Ltd. for **general reference only**. While we endeavour to ensure that the information is as accurate and up-to-date as possible, **no warranty, express or implied, is given** as to its completeness, correctness or fitness for any particular purpose. Raunaq Steels Trading Pvt. Ltd. **accepts no liability** for any loss or damage arising directly or indirectly from the use of, or reliance upon, the information contained herein. For **authoritative and legally binding** specifications, users must refer to the **official publications** of the relevant standards—such

as the BIS, ASTM, EN or JIS standards—available through their respective websites or published documents