

IRSM 41-97 – Technical Datasheet

1. Chemical & Mechanical Properties

A. Chemical Composition

Element	% Composition
Carbon (C)	≤ 0.19%
Silicon (Si)	0.15 – 0.65%
Manganese (Mn)	0.70 – 1.50%
Phosphorus (P)	≤ 0.035%
Sulphur (S)	≤ 0.040%
Copper (Cu)	0.25 – 0.35%
Chromium (Cr)	0.40 – 0.60%
Nickel (Ni)	≤ 0.25%

B. Mechanical Properties

Property	Value
Yield Strength (YS)	≥ 345 MPa (t ≤ 20 mm)
Tensile Strength (TS)	470 – 630 MPa
Elongation	≥ 22 % (≤16 mm)
Impact Toughness	≥ 27 J @ -20 °C

2. Equivalent / Alternative Grades

Standard	Grade	YS (MPa)	TS (MPa)
ASTM A588	Grade B	345	485 – 630
EN 10025-5	S355J2W	355	470 – 630
JIS G3114	SMA490AW	365	490 – 610

3. Common Applications

- Coach & wagon body shells
- Trough floors and side panels
- Weather-resistant bridge components

4. Standard Conformance

Conforms to Indian Railways IRS:M-41 (1997).

Weathering structural steel with copper, chromium and nickel additions to enhance corrosion resistance.

5. Disclaimer

All chemical compositions, mechanical properties, dimensions and other technical data presented on this page are provided by Raunaq Steels Trading Pvt. Ltd. for **general reference only**. While we endeavour to ensure that the information is as accurate and up-to-date as possible, **no warranty, express or implied, is given** as to its completeness, correctness or fitness for any particular purpose. Raunaq Steels Trading Pvt. Ltd. **accepts no liability** for any loss or damage arising directly or indirectly from the use of, or reliance upon, the information contained herein. For **authoritative and legally binding** specifications, users must refer to the **official publications** of the relevant standards—such as the BIS, ASTM, EN or JIS standards—available through their respective websites or published documents