

# IS1079 HR4 – Technical Datasheet

## 1. Chemical & Mechanical Properties

### A. Chemical Composition (Max %)

Element	Max %
C	0.12
Mn	1.50
P	0.040
S	0.040

### B. Mechanical Properties (Typical / Min)

Property	Value
Yield Strength	≥ 180 MPa
Tensile Strength	320–360 MPa
Elongation	≥ 32 %

## 2. Equivalent / Alternative Grades

Standard	Grade
EN 10111	DD14
JIS G3132	SPHT3

### 3. Common Applications

- Extra-deep drawing
- Automotive body parts
- White-goods panels

### 4. Standard Conformance

Conforms to IS 1079 : 2017 – Hot-Rolled Carbon-Steel Sheet, Plate and Strip grades.

### 5. Disclaimer

All chemical compositions, mechanical properties, dimensions and other technical data presented on this page are provided by Raunaq Steels Trading Pvt. Ltd. for **general reference only**. While we endeavour to ensure that the information is as accurate and up-to-date as possible, **no warranty, express or implied, is given** as to its completeness, correctness or fitness for any particular purpose. Raunaq Steels Trading Pvt. Ltd. **accepts no liability** for any loss or damage arising directly or indirectly from the use of, or reliance upon, the information contained herein.

For **authoritative** and **legally binding** specifications, users must refer to the **official publications** of the relevant standards—such as the BIS, ASTM, EN or JIS standards—available through their respective websites or published documents.