

ISC490Y – IS 513 Part 2 (2016) – Dual-Phase- Technical Datasheet

1. Chemical & Mechanical Properties

Property	Value
C (%)	≤0.10
Mn (%)	≤2.00
Si (%)	≤0.50
P (%)	≤0.020
S (%)	≤0.020
Al (%)	0.02–0.06
Ti (%)	≤0.15
Nb (%)	≤0.09
Cu (%)	—
Cr (%)	—
Yield Strength YS (MPa min)	490
Tensile Strength UTS (MPa min)	550
Elongation A80 (%) min	22

2. Equivalent / Alternative Grades

Grade	Standard	C%	Mn %	Si%	P%	S%	Al %	Ti %	Nb %	Cu %	Cr %	UTS/YS
ASTM Gr 490	ASTM A1008	≤0.10	≤2.00	≤0.50	≤0.020	≤0.020	0.02–0.06	≤0.15	≤0.09	—	—	YS 490 / UTS 550
EN Gr 490	EN 10268	≤0.10	≤2.00	≤0.50	≤0.020	≤0.020	0.02–0.06	≤0.15	≤0.09	—	—	YS 490 / UTS 570
JFS Gr 490	JFS A2001	≤0.10	≤2.00	≤0.50	≤0.020	≤0.020	0.02–0.06	≤0.15	≤0.09	—	—	YS 490 / UTS 580

3. Common Applications

- Automotive structural parts
- High-strength formed panels
- Chassis components

4. Standard Conformance

Cold-reduced sheet/strip conforming to IS 513 Part 2 (2016).

5. Disclaimer

All chemical compositions, mechanical properties, dimensions and other technical data presented on this page are provided by Raunaq Steels Trading Pvt. Ltd. for **general reference only**. While we endeavour to ensure that the information is as accurate and up-to-date as possible, **no warranty, express or implied, is given** as to its completeness, correctness or fitness for any particular purpose. Raunaq Steels Trading Pvt. Ltd. **accepts no liability** for any loss or damage arising directly or indirectly from the use of, or reliance upon, the information contained herein. For **authoritative** and **legally binding** specifications, users must refer to the **official publications** of the relevant standards—such as the BIS, ASTM, EN or JIS standards—available through their respective websites or published documents