



RAUNAQ
— TRUSTED STEEL —

Fe 415D – Technical Datasheet

1. Chemical & Mechanical Properties

Element	% Composition
C (%)	0.25
S (%)	0.045
P (%)	0.045
S+P (%)	0.085
Yield (MPa)	415
Yield (MPa)	565
Elongation (%)	18

2. Equivalent / Alternative Grades

Grade	Standard	Yield (MPa)	Tensile (MPa)	Carbon Max (%)
ASTM A615 Grade 60	ASTM A615	420	620	0.30
BS 4449 B460C	BS 4449	460	540	0.25
ISO 6935 B500A	ISO 6935-2	500	575	0.24

3. Common Applications

- General residential & low-rise buildings

- Slabs, beams & columns in moderate load

4. Standard Conformance

IS 1786:2008 (incl. latest amendments)

5. Disclaimer

All chemical compositions, mechanical properties, dimensions and other technical data presented on this page are provided by Raunaq Steels Trading Pvt. Ltd. for **general reference only**. While we endeavour to ensure that the information is as accurate and up-to-date as possible, **no warranty, express or implied, is given** as to its completeness, correctness or fitness for any particular purpose. Raunaq Steels Trading Pvt. Ltd. **accepts no liability** for any loss or damage arising directly or indirectly from the use of, or reliance upon, the information contained herein.

For **authoritative** and **legally binding** specifications, users must refer to the **official publications** of the relevant standards—such as the BIS, ASTM, EN or JIS standards—available through their respective websites or published documents.